

Features

NEW! CMYK color matching now available for Tabbed Metal Barcode Nameplates at NO ADDITIONAL CHARGE!
Photographically reproduced black copy, logos and bar codes ensure accurate and reliable reads
Anodizing process protects black copy, logos and bar codes from chemicals, abrasion and high temperatures
Adhesives specially matched to surface for maximum adhesion or optional holes available for mechanical fasteners
Optional intensification process increases heat resistance and improves the image resistance for other environmental conditions
Break-away tab for easier liner removal

Product Print Options

Barcode . Data Matrix . QR Code . Serial Number . Text

Product Functionality

Abrasion Resistance . Chemical Resistance . Heat Resistance

Popular Applications

Audio / Visual . Government . Inventory . Oil & Gas . Restoration . Transportation / Logistics . Utilities . Warehouse / Distribution Centers . Wineries / Breweries . Churches . Construction / Tool Tracking . Hospitals . IT Assets . Manufacturing



Category

PHA 5 Point Promise . Manufacturing .
Information Technology . Medical . Utilities
. Warehouse . Equipment Rental .
Education . Asset Tracking . Tool Tracking
. Work-in-Process . Metal Asset Tags .
Metal Barcode Nameplates

Tabbed Metal Barcode Nameplates have a convenient break-away tab to assist with liner removal.

Ask about our Photo Anodized 5 Point Promise!

These nameplates combine reliability with the durability you have come to expect from any Metalcraft product. They have consistently remained one of our most popular products for our customers due to their dependability as well as the options available. These include the thickness of the material, adhesive options and size selection. Optional second colors are digitally inkjet printed.

For more information, check out our blog, [Tabbed Metal Asset Tags](#) or our case study, [Keeping Tabs on Traffic Signs](#).

Tabbed Metal Barcode Nameplates

Specifications Data

Material	.012" thick matte anodized aluminum is standard. Optional thicknesses include .020".
Serialization	All alphanumeric bar codes are photo imaged with a human-readable equivalent. Guaranteed no skips in sequence. Code 39 with 2.7 to 9.4 characters per inch (CPI) is standard. Other bar code symbologies including Code 128, I 2 of 5, 2D DataMatrix and QR Code.
Label Copy	Printed copy may include block type, stylized type, logos or other designs. Black copy is produced photographically. Colors other than black are screen printed.
Colors	Choose black only or one of our standard colors (red, blue, green, or yellow) for block style type, stylized type, logos or other designs. Due to the contrast needed for bar code scanner, all bar codes are black. Color samples available upon request.
Standard Adhesive	.0035" thick, pressure-sensitive adhesive that has a very high peel strength and provides excellent resistance to heat and chemicals.
Sizes	Various sizes available
Holes	Optional
Packaging	Shipped in "workout-of" cartons for convenient application. Both cartons and trays clearly marked to indicate serial numbers of contents. Pressure-sensitive adhesive orders shipped with cleaner and application instructions.
Shipment	5-10 business days

Chemical Testing

Chemical Test Data

Characteristics	Test Conditions	Effect
Water/Humidity		no effect
Salt spray	5% at 95°F, 700 hours	no effect
Ammonium hydroxide	2 hours at 1% and 5%	slight dulling of image, affects overall readability
Ethyl alcohol		no effect
Ferric chloride	10%, 16 hours	no effect
Heptane	72 hours	no effect
Hydrocarbon fluid		no effect
JP-4 fuel		no effect
Kerosene		no effect
Methyl ethyl ketone		no effect
Nitric acid	1%, 40 hours	no effect
Phosphoric acid	1%, 40 hours	no effect
Skydrol		no effect
Sodium hydroxide		affects overall readability
sulfuric acid	10%, 24 hours	no effect
Turbine and jet fuel (MIL-L 5161C)	(MIL-L 5161C)	no effect
Tetra sodium pyrophosphate	1%, 40 hours	no effect
Trisodium phosphate		no effect

Destructive Testing

Destructive Test Data

Image intensified

Weatherometer, 20 years equivalent

Reduced overall readability after these thresholds

Temperature Testing

Temperature Test Data

Read Range Testing

Read Range Test Data

Barcode Readability Testing

Barcode Readability Test Data

Abrasion Testing

Abrasion Test Data

Image Intensified	Plates brushed for 7000 cycles with stiff nylon wheel (C-17) at a 1000 gm (16 ox.) load	Reduced overall readability after these thresholds
-------------------	---	--

Label Adhesion Testing

Label Adhesion Test Data

Pull Testing

Pull Test Data