


# QuickTab Metal Asset Tag Dispenser



The QuickTab Tag Dispenser is a revolutionary, patent-pending product from Metalcraft designed to make nameplate application more efficient than any other product on the market.

We've combined our tabbed nameplate with a specially designed metal cable to provide a more automated process for applying adhesive-backed nameplates.

The most expensive and often overlooked component of implementing an asset tracking system is the labor lost of applying the tags. As much as 2.8x faster than standard nameplate application, the ring provides huge labor savings potential. The ring provides efficiency by pulling at the tab to easily peel the liner away from the nameplate. The ring provides several benefits: labor cost savings, eliminates risk of adhesive contamination, collects the scrap, transferability when multiple people are part of the application process and keeping serial numbers in order.

## Features

Ring provides 5 major benefits over traditional nameplate application  
Adhesives specially matched to surface for maximum adhesion  
Available in three standard sizes, with thicknesses ranging from .005" to .020" anodized aluminum  
Break-away tab for easier liner removal  
Optional Teflon® Coating available for extreme environments

## Product Print Options

Barcode . Data Matrix . QR Code . Serial Number . Text

## Product Functionality

Abrasion Resistance . Chemical Resistance . Heat Resistance

## Popular Applications

Government . Inventory . Oil & Gas . Restoration . Warehouse / Distribution Centers . Churches . Construction / Tool Tracking . Hospitals . IT Assets . Schools

## Category

Metal Asset Tags

# QuickTab Metal Asset Tag Dispenser

## Specifications Data

**Material** Standard thicknesses include .005", .008", .012", and .020".

**Serialization** All alphanumeric bar codes are photo imaged with a human-readable equivalent. Guaranteed no skips in sequence. Code 39 with 2.7 to 9.4 characters per inch (CPI) is standard. Other bar code symbologies including Code 128, I 2 of 5, 2D DataMatrix and QR Code.

**Label Copy** The printed label copy may include block type, stylized type, logos or other designs. All black copy is produced photographically. Colors other than black are screen printed.

**Colors** Choose from our standard colors (black, blue, red, green or yellow). Additional color options, as well as custom colors, are available. Metalcraft color samples available upon request.

**Standard Adhesive** Pressure-sensitive acrylic adhesive

**Sizes** Various sizes available

**Packaging** Shipped on rings for convenient application. Each flat consists of one or more rings containing sequentially packed nameplates. Flats will come in cartons. Rings are clearly marked to indicate serial numbers of contents. Pressure-sensitive adhesive orders are shipped with a roller, cleaner, and application instructions. Roller is recommended when applying nameplates.

**Shipment** 8-13 business days

# QuickTab Metal Asset Tag Dispenser

## Chemical Testing

### Chemical Test Data

Characteristics	Test conditions	Effect
Water/humidity		no effect
Salt spray	5% at 95°F, 700 hours	no effect
Ammonium hydroxide	2 hours at 1% and 5%	Slight dulling of image, affects overall readability
Ethyl alcohol		no effect
Ethyl acetate	24 hours	no effect
Ferric chloride	10%, 16 hours	no effect
Heptane	72 hours	no effect
Hydrocarbon fluid		no effect
JP-4 Fuel		no effect
Kerosene		no effect
Methyl Ethyl Ketone		no effect
Nitric acid	1%, 40 hours	no effect
Phosphoric acid	1%, 40 hours	no effect
Skydrol		no effect
Sodium hydroxide		affects overall readability
Sulfuric acid	10%, 24 hours	no effect
Turbine and jet fuel (MIL-L 5161C)	(MIL-L 5161C)	no effect
Tetra sodium pyrophosphate	1%, 40 hours	no effect
Trisodium phosphate		no effect

## Destructive Testing

An tag with an intensified image was tested in the weatherometer, 20 years equivalent; reduced overall readability after these thresholds.

## **Temperature Testing**

An tag with an intensified image was tested for 265 hours at 500°F, 90 hours at 600°F, 60 hours at 700°F; reduced overall readability after these thresholds.

## **Abrasion Testing**

A plate with an intensified image was brushed for 7,000 cycles with stiff nylon wheel (C-17) at a 1,000 gm (16 ox.) load; reduced overall readability after these thresholds.