



Features

Unique coating process that increases temperature range to 1200°F
Photographically reproduced black copy, logos and bar codes ensure accurate and reliable reads
Anodizing process protects black copy, logos and bar codes from chemicals, abrasion and high temperatures

Product Print Options

Barcode . Data Matrix . QR Code . Serial Number . Text

Product Functionality

Abrasion Resistance . Chemical Resistance . Heat Resistance . UV/Outdoor Durability

Popular Applications

Oil & Gas . Manufacturing

Category

Metal Asset Tags

Metalcraft High Temperature Metal Bar Code Nameplates can really take the heat. Made of durable anodized aluminum, these nameplates are ideal for applications with temperature requirements from 900°F-1200°F. And because it is made out of anodized aluminum our High Temperature Metal Bar Code Nameplates have many of the same benefits that our standard metal bar code nameplates do including an image that is sealed within the anodic layer of the aluminum protecting it from abrasion, solvents and chemicals.

These unique nameplates are an economical alternative to other more expensive high temperature materials such as ceramic and stainless steel. Possible uses include work-in-process tracking or product identification. Due to the high temperatures this product is exposed to, adhesives are not recommended, rather the nameplates should be produced with holes and attached with mechanical fasteners.

Specifications Data

Material .008" thick matte anodized aluminum is standard. Optional thicknesses include: .012", .020", and .032".

Serialization All alphanumeric bar codes are photo imaged with a human-readable equivalent. Guaranteed no skips in sequence. Code 39 with 2.7 to 9.4 characters per inch (CPI) is standard. Other bar code symbologies including Code 128, I 2 of 5, 2D DataMatrix and QR Code. OCR characters and CPIs also available.

Label Copy The printed nameplate copy is block type only. No stylized type, logos or other designs available. All copy is photo imaged.

Colors Available in black only

Sizes Various sizes available

Holes Various sizes available

Packaging Shipped in "work-out-of" cartons for convenient application. Each carton consists of one or more plastic trays containing 250 sequentially packed nameplates (can vary with metal thickness). Both cartons and trays are clearly marked to indicate serial numbers of contents.

Shipment 20-25 business days

Chemical Testing

Chemical Test Data

Characteristics	Test conditions	Effect
Water/humidity		no effect
Salt spray	5% at 95°F, 700 hours	no effect
Ammonium hydroxide	2 hours at 1% and 5%	Slight dulling of image, affects overall readability
Ethyl alcohol	72 hour immersion	no effect
Ethyl acetate	24 hour immersion	no effect
Ferric chloride	10%, 16 hours	no effect
Heptane	72 hours	no effect
Hydrocarbon fluid	1 hour immersion	no effect
JP-4 fuel	72 hour immersion	no effect
Kerosene	12 hour immersion	no effect
Methyl ethyl ketone	24 hour immersion	no effect
Nitric acid	1%, 40 hours	no effect
Phosphoric acid	1%, 12 hours	no effect
Skydrol	24 hr immersion (room temp & boiling)	no effect
Sodium hydroxide	1%, 1 hour	affects overall readability
Sulfuric acid	10%, 24 hours	no effect
Turbine and jet fuel (MIL-L 5161C)	(MIL-L 5161C)	no effect
Tetra Sodium Pyrophosphate	1%, 40 hours	no effect
Trisodium Phosphate	1%, 40 hours	no effect

Destructive Testing

Destructive Test Data

Image Intensified

Weatherometer, 20 years equivalent

Reduced overall readability after these thresholds

Temperature Testing

Temperature Test Data

Image intensified

168 hours at 1000°F; max temp 1200°F

Reduced overall readability after these thresholds

Abrasion Testing

Abrasion Test Data

Image intensified

Plates brushed for 7,000 cycles with stiff nylon wheel (C-17) at a 1,000 gm (16 oz.) load

Reduced overall readability after these thresholds
