

Stick & Staple RFID Tag



Perfect for applications that need a bit more than just adhesive, Metalcraft's Stick & Staple RFID Tag attaches directly to assets with adhesive with the added option of stapling the tag, ensuring the tag stays attached to those hard-to-adhere surfaces while not damaging the inlay. Ideal for wood and cardboard applications, the tag's construction protects the inlay by sealing it from environmental conditions that could affect the performance of the RFID tag while subsurface printing includes variable data such as bar code and/or human readable numbers. All Metalcraft RFID tags are designed with our proven durability, ready to withstand repeated usage in rugged environments, generating a greater ROI for your business. Each tag can be programmed to match the variable information printed on the label and digital printing allows limitless color and design options.

Features

Ideal for applications involving wood (pallets, crates, barrels, etc) or cardboard
Digital printing process provides for greater print capability with logos or special designs, ensuring crisp details on even the most complex logos for maximum clarity.
Meets EPCglobal Gen2 (V 1.2.0) as well as ISO/IEC 18000-6C:2004/Amd 1:2006 (type C and update of Types A and B).

Product Print Options

Barcode . Data Matrix . QR Code . RFID . Serial Number . Text

Product Functionality

Abrasion Resistance . Chemical Resistance

Popular Applications

Inventory . Wineries / Breweries . Construction / Tool Tracking . Manufacturing

Category

RFID Pallet Tags . RFID Tags

Specifications Data

Material **2.3 white mil polypropylene**

Serialization Bar code and human-readable equivalent is produced using the latest high-resolution digital technology available, which provides excellent clarity and easy scanning. Code 39 is the standard symbology with a range of 2.7 to 9.4 CPI (characters per inch). Optional symbology is Code 128, I 2 of 5, 2D DataMatrix and QR Code.

Label Copy The label copy may include block type, stylized type, logos or other designs. All copy, block type, stylized type, logos, designs, and bar code are subsurface printed. This unique process provides excellent resistance to solvents, caustics, acids and moderate abrasion.

Colors Standard colors include black, red, yellow, green, dark blue, orange, purple or blue. Custom spot colors are also available at no additional charge. Due to contrast needed for the bar code scanner, all bar codes are black.

Standard Adhesive Permanent acrylic adhesive

Frequency Range UHF = 860-960 MHz; HF = 13.56 MHz

Sizes 4" x 2" (size must include a 1/2" blank border on all sides to protect inlay from staples)

Packaging Produced and shipped in roll form.

Shipment 14 business days

Chemical Testing

Tags were applied to glass panels at room temperature conditions and immersed in the chemicals noted below for 48 hours. Results are noted below.

Chemical Test Data

Length of immersion	5% salt water	Glass cleaner	Bathroom cleaner	Isopropyl Alcohol 99%	Diesel Fuel	NaOH pH12.0	HCK pH 1.0	Brake fluid
2 Hours	no effect	no effect	no effect	no effect	adhesive ooze	no effect	no effect	no effect
24 hours	no effect	no effect	no effect	no effect	no effect	no effect	no effect	no effect
48 hours	no effect	no effect	no effect	no effect	no effect	no effect	no effect	no effect

Destructive Testing

Burst strength - 1" wide strip of the tag that included the inlay was stapled to a wooden block and peeled at 180 degrees/12 inches per minute with the iMass SP-2100 peel and adhesion tester. Goal was to determine the static peak peel value at the point the staple pulled through the tag to determine a burst strength or tensile strength value of durability. A burst strength of more than 10 lbs. was needed to affect the tag.

Temperature Testing

Sample showed no deterioration after being subject to -40°F for 24 hours, and the inlay was still readable with an Alien ALH-9000 handheld reader prior to removal from the freezer. Samples showed no deterioration when exposed to 150°F, 200°F, and 250° for 1 hour each. Sample started showing discoloration after exposure to 300°F for 1 hour, and melted after exposure to 350°F for 1 hour. The inlay was readable after exposure to 300°F, but was not readable after exposure to 350°F.

Read Range Testing

Theoretical read ranges in the Voyantic anechoic chamber based on Alien Squiglette H4 inlay.

Read Range Test Data

Stick & Staple RFID Tag Anechoic Chamber Results

Wood	Glass	Plastic	Cardboard
25 ft	5 ft	34 ft	21 ft