



This patent-pending RFID security tag product combines the durability of our standard RFID tag with destructible features that render the label useless if it is removed or tampered with. Its specialized construction eliminates the transferability of the RFID tag and incorporates two levels of destructibility. If someone attempts to remove the tag the RFID antenna construction breaks into separate pieces making the read range of the tag mere inches. If a person tries to reassemble the tag to make it functional, the portion that is still adhered to will literally disintegrate if an attempt is made to remove it from the object.

The plastic surface mount DuraDestruct UHF RFID tags are part of the DuraDestruct line of tamper/security tags that also includes glass surface mount RFID tags.

## Features

Ideal for security and tamper proof RFID applications  
Deters transferability as tag is rendered useless upon removal  
Provides additional levels of security for RFID anti theft and RFID protection systems  
Perfect for plastic bins, totes, tubs and crates  
Read range up to 40' on plastic  
Custom printing available  
Patent pending product

## Product Print Options

Barcode . Data Matrix . QR Code . RFID . Serial Number . Text

## Product Functionality

Abrasion Resistance . Chemical Resistance . Heat Resistance . UV/Outdoor Durability

## Popular Applications

Bins/Crates/Totes . Non-metal surfaces . Returnable containers . Security applications

## Category

RFID Pallet Tags . RFID Tags . Tamper Proof

## Specifications Data

Material	Polyester
Serialization	Bar code and human-readable equivalent are produced using the latest high-resolution digital technology available, which provides excellent clarity and easy scanning. Code 39 is the standard symbology with a range of 2.7 to 5.4 CPI (characters per inch). Optional symbology is Code 128.
Label Copy	The label copy may include block type, stylized type, logos or other designs
Colors	Standard colors include black, red, yellow, green, dark blue, orange, purple or blue. Custom spot colors are also available at no additional charge. Due to contrast needed for the bar code scanner, all bar codes are black.
Standard Adhesive	Pressure-sensitive acrylic adhesive
Frequency Range	Worldwide UHF RFID Operation (840 – 960 MHz)
Sizes	4" x 1"
Packaging	Produced and shipped in roll form
Shipment	14 business days

## Chemical Testing

Samples applied to glass panels, allowed to wet out for 72 hours, immersed in chemicals below at ambient room temperature conditions. Inlays in all samples still reading after 48 hours of exposure. Key: NE = No effect; AO = adhesive ooze; PE = print erosion under laminate

### Chemical Test Data

	Water	Salt Water 5% NaCl	Bathroom Cleaner	Glass Cleaner Windex Commercial Line	Isopropanol 99%	Brake Fluid DOT 3	Acetone	Diesel Fuel	Nitric Acid pH 1.0 +/- 0.01	Hydrochloric Acid pH 1.0 +/- 0.01	Sodium Hydroxide pH 12.0 +/- 0.01
2 hours	NE	NE	NE	NE	AO	AO	AO	AO	NE	NE	NE
24 hours	NE	NE	NE	NE	AO	AO	AO	AO	NE	NE	NE
48 hours	NE	NE	NE	PE	AO	AO	AO	AO	NE	NE	NE

## Temperature Testing

Samples applied to glass panels at ambient room temperature conditions, sit for 72 hours, then placed in freezer set to -40F for 24 hours. All inlays reading prior to removal from the freezer, all tags still destructible prior to removal from the freezer. Samples then exposed to each temperature noted below for 1 hour. All tags still destructible while at 200F. Inlays quit reading after exposure to 400F. Key: NE = no effect; TD = Sample materials discolored; TP = Sample print degradation; TM = Tag melted/destroyed; SS = sample shrinking; adhesive ooze at edges

### Temperature Test Data

200°	250°	300°	350°	400°	450°	500°
NE	NE	NE	SS	TD, SS	TP, TD, SS	TM

## Read Range Testing

### Read Range Test Data

DuraDestruct Voyanic Anechoic Chamber test results

Substrate	ETSI	FCC
Windshield glass	28.68	34.7
Tempered glass	27	30.25
Polypropylene	45.98	40.36
HDPE	37.5	50.5
Wood	30.5	29.5
Corrugated Paper	42.5	47.5